

IF ANY NICUAL (K-MONEL) MATERIAL IS UTILIZED IN THIS ORDER, IT MUST BE IN ACCORDANCE WITH ONE OF THE FOLLOWING MODIFICATIONS:

A). QQ-N-286 REVISION F, DATED 29 NOVEMBER 1990, AND HAVE BEEN PRODUCED ONLY BY SPECIAL METALS CORPORATION (FORMERLY INCO ALLOYS INTERNATIONAL/HUNTINGTON ALLOYS INC) WITH A PRODUCTION (POUR) DATE LATER THAN DECEMBER 21, 1976.

TEST REPORTS ARE REQUIRED SHOWING ACTUAL RESULTS OF ALL CHEMICAL ANALYSES. MECHANICAL PROPERTY TESTS, AND MECHANICAL TESTING REQUIRED BY THE SPECIFICATION FOR EACH HEAT AND LOT OF MATERIAL FURNISHED.

FIRST ARTICLE TESTING PER PARAGRAPH 3.1 OF QQ-N-286 REVISION F IS REQUIRED FOR ALL HEATS PRODUCED AFTER FEBRUARY 19, 2001. SPECIAL METALS CORPORATION WAS EXEMPT FROM FIRST ARTICLE TESTING FOR ALL HEATS PRODUCED PRIOR TO FEBRUARY 19, 2001.

B). REVISION G, WITH THE FOLLOWING MODIFICATIONS:

REVISE PARAGRAPH 4.2.2.2 OF QQ-N-286G AS FOLLOWS:

4.2.2.2 SLOW STRAIN RATE TENSILE TESTS. THREE SPECIMENS SHALL BE PREPARED AND TESTED PER LOT. SPECIMENS SHALL BE TAKEN AFTER THE FINAL HEAT TREATMENT. WHEN MATERIAL IS SHIPPED IN THE ANNEALED CONDITION, SPECIMENS MAY BE TAKEN AFTER THE FINAL ANNEAL AND SHALL BE HEAT TREATED IN ACCORDANCE WITH 4.3.6.1.

4.2.2.2.1 BAR, ROD AND FORGINGS. SLOW STRAIN RATE TENSILE TEST SPECIMENS SHALL BE TAKEN FROM ONE END OF A BAR, ROD, OR FORGING AT THE QUARTER DIAMETER (HALF RADIUS) AND IN THE LONGITUDINAL DIRECTION.

BAR, RODS OR FORGINGS TOO SMALL TO HAVE A SLOW STRAIN RATE TEST SPECIMEN TAKEN FROM THE QUARTER DIAMETER THAT ARE TAKEN FROM A LOT (SEE 4.2.1.3) THAT DOES NOT HAVE ANY LARGER SIZES SHALL HAVE THE SPECIMENS TAKEN FROM THE CENTER AND IN THE LONGITUDINAL DIRECTION.

BAR, RODS OR FORGINGS TOO SMALL TO HAVE A SLOW STRAIN RATE TEST SPECIMEN TAKEN FROM THE CENTER THAT ARE TAKEN FROM A LOT (SEE 4.2.1.3) THAT DOES NOT HAVE ANY LARGER SIZES SHALL BE TAKEN FROM THE HEAT AT THE LATEST INTERMEDIATE ROLLING OR FORGING STEP THAT A SLOW STRAIN RATE TEST SPECIMEN CAN BE

TAKEN FROM THE MID-RADIUS AND HEAT TREATED USING THE SAME HEAT TREATMENT PROCEDURES USED ON THE PRODUCTION HEAT.

4.2.2.2.2 WIRE. SLOW STRAIN RATE TENSILE TEST SPECIMENS SHALL BE TAKEN FROM THE HEAT AT THE LATEST INTERMEDIATE ROLLING OR FORGING STEP THAT A SLOW STRAIN RATE TEST SPECIMEN CAN BE TAKEN FROM THE MID RADIUS AND HEAT TREATED USING THE SAME HEAT TREATMENT IN ACCORDANCE WITH 4.3.6.1.

4.2.2.2.3 SHEET AND PLATE. SLOW STRAIN RATE TENSILE TEST SPECIMENS SHALL BE TAKEN FROM ONE END OF A PLATE AT THE QUARTER THICKNESS AND IN THE LONGITUDINAL DIRECTION. PLATE TOO SMALL TO HAVE A SLOW STRAIN RATE TEST SPECIMEN TAKEN FROM THE QUARTER THICKNESS MAY HAVE THE SPECIMENS TAKEN FROM THE CENTER AND IN THE LONGITUDINAL DIRECTION. SHEET AND PLATE TOO SMALL TO HAVE A SLOW STRAIN RATE TEST SPECIMEN TAKEN FROM THE CENTER MAY HAVE THE SPECIMENS TAKEN AT THE LATEST INTERMEDIATE ROLLING STEP THAT A SLOW STRAIN RATE TEST SPECIMEN CAN BE TAKEN FROM THE QUARTER THICKNESS.

REVISE PARAGRAPH 4.3.6.4.4 OF QQ-N-286G AS FOLLOWS:

4.3.6.4.4 TESTING LABORATORY: SLOW STRAIN RATE TENSILE TESTING SHALL BE PERFORMED BY A NAVSEA APPROVED TEST LABORATORY. THE FOLLOWING IS A LISTING OF THE CURRENTLY APPROVED TEST LABORATORIES, ANY ONE OF WHICH MAY BE USED AT THE VENDOR'S DISCRETION.

HUNTINGTON ALLOYS,
A SPECIAL METALS COMPANY
ATTN: FRANK VELTRY

3200 RIVERSIDE DRIVE
HUNTINGTON, WV 25705

METALLURGICAL CONSULTANTS, INC.
ATTN: W.M. BUEHLER
4820 CAROLINE
P.O. BOX 88046
HOUSTON, TX 77288-0046

NAVAL SURFACE WARFARE CENTER,
CARDEROCK DIV.
ATTN: CHARLES ROE
CODE 614
9500 MACARTHUR BLVD.
WEST BETHESDA, MD 20817-5700

ATI ALLVAC-ALLEGHENY TECHNOLOGIES INC.

ATTN: DR. W.D. CAO
2020 ASHCRAFT AVE.
MONROE, NC 28110

MANNESMANN ROHRENWERKE
MANNESMANN FORSCHUNGSINSTITUT (MFI)
ATTN: DR. WEISS
POSTFACH 251160
47251 DUISBURG
GERMANY

WESTMORELAND MECHANICAL TESTING & RESEARCH, INC.

OLD ROUTE 30, WESTMORELAND DRIVE
P.O. BOX 388 WESTMORELAND DRIVE
YOUNGSTOWN, PA 15696-0388

REVISE PARAGRAPH 6.2 S) AS FOLLOWS:

S) THE LABORATORY CONDUCTING THE SLOW STRAIN RATE TESTING
SHALL BE ONE APPROVED BY NAVSEA (SEE 4.3.6.4.4).

NOTE: FIRST ARTICLE TESTING INVOKED ELSEWHERE IN THIS PURCHASE
ORDER DOES NOT APPLY TO MATERIAL PRODUCED IN ACCORDANCE WITH
REVISION G OF QQ-N-286.