

ALL MATERIAL DELIVERED UNDER THIS ORDER MUST BE PRODUCED IN ACCORDANCE WITH AND MEET THE REQUIREMENTS OF ELECTRIC BOAT CORPORATION SPECIFICATION 2678G WITH THE FOLLOWING MODIFICATION:

PARAGRAPH 2.4, PAGE 11

DELETE: "IN ADDITION, ONE COPY SHALL BE MAILED TO THE COGNIZANT PURCHASING BUYER"

NOTE: WHENEVER REFERENCE IS MADE TO NAVSEA 0900-070-6010, ALL REQUIREMENTS APPLICABLE TO BUYER SUPPLIERS ARE CONTAINED IN ELECTRIC BOAT SPECIFICATION 2678G. SUPPLIERS SHOULD NOT ATTEMPT TO OBTAIN A COPY OF NAVSEA 0900-070-6010.

ALL REPAIR WELDING OF BASE MATERIALS SHALL BE ACCOMPLISHED IN ACCORDANCE WITH EB-4186 REVISION D.

APPENDIX A, PARAGRAPH 7.2, PAGE 31

THE FOLLOWING ADDITIONAL REQUIREMENT APPLIES:

STATEMENTS ON MATERIAL CERTIFICATION DOCUMENTS MUST BE POSITIVE AND UNQUALIFIED. WORDS SUCH AS 'TO THE BEST OF OUR KNOWLEDGE' OR 'WE BELIEVE THE INFORMATION CONTAINED HEREIN IS TRUE' ARE NOT ACCEPTABLE.

APPENDIX B, PAGE 33

DELETE THE DEFINITION OF HOMOGENEOUS LOT AND REPLACE THE FOLLOWING:

A GROUP OF LIKE ITEMS THAT ARE PRODUCED IN A COMMON HEAT OR BATCH, OR ARE PRODUCED UNDER CONTINUOUS CAST OR POUR PROCESS WITH THE SAME VENDOR TRACEABILITY NUMBERS, ARE OF THE SAME NOMINAL SIZE, AND ARE RECEIVED IN A SINGLE SHIPMENT. FOR BATCH OR CONTINUOUS CAST/POUR PROCESSES, SAMPLES FOR CHEMICAL AND MECHANICAL PROPERTIES SHALL BE TAKEN NO LESS THAN ONCE IN EVERY EIGHT HOURS OF OPERATION. IF ADDITIONAL PRODUCTION PROCESSES ARE UTILIZED THAT ALTER THE MECHANICAL PROPERTIES OF THE MATERIAL (E.G.,

HEAT-TREAT, COLD OR HOT FORGE, EXTRUSION), THEN ALL ITEMS OF THE SAME "HEAT" NUMBER AND ADDITIONALLY PROCESSED UNDER THE SAME CONDITIONS AT THE SAME TIME SHALL BE CONSIDERED AS A HOMOGENEOUS LOT.