

If the valve is installed during welding, weld in halves using 125 F interpass temperature. Mid- position the stem / disc. Follow the "Reduced Heat Input / Cooling Methods" section of W-91 Appendix A or W-93 Appendix A, as applicable. For mechanized welding, see Appendix B.