

## W1310-19960324

PHYSICAL PROPERTIES SHALL BE:

1. DENSITY - 65 TO 80 GM/CC.
2. PERMEABILITY (AFS UNITS) - 18 MINIMUM.
3. TRANSVERSE STRENGTH OF ONE INCH SQUARE BAR - 100 PSI MINIMUM.
4. HEAT TRANSFER - TOTAL HEAT LOSS THROUGH ONE INCH THICKNESS AFTER ONE HOUR: HOT FACE AT 1400 DEGREE C., COLD FACE RADIATING TO SURROUNDINGS 1200 CALORIES SQ. CM MAX. FOR KALMINEX SLEEVES: 1500 CALORIES SQ. CM FOR KALFAX SLEEVES.

SLEEVES TO CONTAIN NO ASBESTOS.

SLEEVES TO BE PALLETIZED AND SHIPPED IN SUCH A MANNER AS TO BE PROTECTED FROM THE ELEMENTS (RAIN, SNOW, ETC.) AND TO AVOID BREAKAGE DURING NORMAL HANDLING IN SHIPMENT.