

Coded Note Number: **Y1070**

Revision: **C001**

Date: **August 24, 2015**

Title: **PITTING AND CORROSION REQUIREMENTS**

The depth of worked-in scale, pits, corrosion or other defects shall not exceed 0.025 inch or result in an under gauge condition. Isolated, individual pits up to 0.035 inch deep shall be acceptable provided the pits are not within six inches of each other, and do not result in an under gauge condition.