

Y2240  
Revision Level A  
Revision Date August 14, 2000  
STEEL PLATE SAMPLING

Y2240-20000814

FOR PLATE MATERIAL ORDERED TO MIL-S-16216 AND

MIL-S-24645 SAMPLES FOR CHEMICAL OR SPECTROGRAPHIC ANALYSIS SHALL BE TAKEN FROM THE TOP END, MIDDLE , AND MID-THICKNESS POSITION OF THE TOP PLATE OF EACH INGOT, OR SLAB IN THE CASE OF CONTINUOUS CASTING, IN EACH LOT. SOLID SAMPLES SHALL BE REMOVED FROM THE ROLLING-DIRECTION CENTERLINE OF THE PLATE AT MID-THICKNESS OF THE PLATE.