

Coded Note Number: **Y2240**
Revision: **C001**
Date: **October 16, 2017**
Title: **STEEL PLATE SAMPLING**

This revision history is provided for convenience and does not alleviate the supplier's responsibility with understanding and complying with the full coded note.
Change from Revision A – Editorial change to reformat to current standard.
Bolded font indicates changed/added content.
[Text deleted] inserted in the document indicates the removal of content.

For plate material ordered to MIL-S-16216 and MIL-S-24645 samples for chemical or spectrographic analysis shall be taken from the top end, middle, and mid-thickness position of the top plate of each ingot, or slab in the case of continuous casting, in each lot. Solid samples shall be removed from the rolling-direction centerline of the plate at mid-thickness of the plate.