

Coded Note Number: **Y2290**

Revision: **C001**

Date: **October 16, 2017**

Title: **HSLA-100 STEEL PLATE THICKNESS/CHEMISTRY**

**This revision history is provided for convenience and does not alleviate the supplier's responsibility with understanding and complying with the full coded note.**

**Change from Revision 5095 – Editorial change to reformat to current standard.**

**Bolded font indicates changed/added content.**

**[Text deleted] inserted in the document indicates the removal of content.**

HSLA-100 when ordered to T9074-BD-GIB-010/0300 (Appendix 24645) shall conform to the chemistry of table 1 in accordance with the following requirements for thickness:

Use composition 1. For thickness equal to or greater than 3/16" through 1" (3/16"  $\leq t \leq 1$ "),

Use composition 2. For greater than 1" through 1-5/8" (1"  $< t \leq 1-5/8$ "), and

Use composition 3. For thickness greater than 1-5/8" ( $t > 1-5/8$ ").